

A larger version of the BEYLOS 2329 logo, with "BEYLOS" in a stylized, outlined font and "2329" in a solid, bold font.

Special alloyed steel  
designed for dies,  
moulds, punches  
subjected to high  
working temperature



## General characteristics

BeyLos®2329 is a special alloyed steel designed for the manufacture of dies, moulds, punches and other components subjected to high working temperatures.

The best features of this steel are:

- high resistance to thermal shock and to heat cracking
- good mechanical characteristics in hot condition
- optimal mechanical characteristics in cold condition
- good toughness in hot condition.

BeyLos®2329 is obtained through a special 'super clean' manufacturing process, which allows a high level of micro-purity to be achieved.

BeyLos®2329 is normally supplied in round sections up to 600 mm in diameter, in the annealed condition with hardness values lower than 220 HB, thereby guaranteeing a good machinability.

If subjected to suitable heat treatment, BeyLos®2329 can reach a hardness of 48 HRC without affecting the toughness.

In order to improve further the mechanical characteristics of the surface, BeyLos®2329 can be coated with PVD or PA/CVD methods.

Alternatively it can be hardened through flame hardening, induction tempering or subjected to nitriding.

This allows a hardness value of about 52 HRC to be reached. The hardness of the nitrided layer is about 900-1000 HV.

The high micro-purity and structural homogeneity levels give this grade good suitability to polishing and photo-engraving.

If required, it is possible to carry out welding operations with TIG or MMA methods on dies made of BeyLos® 2329.

BeyLos®2329 is also designed with the aim to guarantee the minimum use of virgin materials, moving toward the use of scrap categories difficult to be recycled, that can become food for the steel making production of BeyLos®2329 grade.

## Chemical analysis

<b>BeyLos®2329</b>			
<b>C [%]</b>	<b>0,44 ÷ 0,54</b>	<b>Alloying [% in weight]</b>	
<b>Si[%]</b>	<b>0,60 ÷ 0,90</b>	<b>Cr[%]</b>	<b>1,70 ÷ 2,10</b>
<b>Mn[%]</b>	<b>0,70 ÷ 1,00</b>	<b>Mo[%]</b>	<b>0,25 ÷ 0,45</b>
<b>Ni[%]</b>	<b>0,50 ÷ 0,80</b>	<b>V [%]</b>	<b>0,15 ÷ 0,25</b>

Table for comparison of international classification

**W. Nr.**            **1.2329**

**DIN**                **46CrSiMoV7**

Lucchini RS's tool steels have been researched and formulated in order to optimize the material performances.

The brand name identifies the Lucchini RS product and the number evokes the Werkstoff classification or other means of reflecting the characteristics of use.

## Main applications:

BeyLos®2329 is suitable for the following applications:

- dies subjected to low pressure
- containers for die-casting presses
- extrusion press blocks
- sleeves for extrusion presses.

## Physical and mechanical properties


### Main physical properties

	20°C	400°C	600°C
<b>Modulus of elasticity [GPa]</b> (1GPa=1000 MPa)	210	186	179
<b>Coefficient of thermal expansion [<math>10^{-6}/K</math>]</b>	-	13,2	14,5
<b>Thermal conductivity [W/mK]</b>	27,0	29,1	32,4

### Main mechanical properties

	at 400°C	at 500°C	at 600°C
<b>Ultimate tensile strength (UTS) [MPa]</b>	1.080	900	440
<b>Yield stress (YS)[MPa]</b>	850	680	270

These are average values obtained on a sample which has been hardened at 870° C, quenched and tempered at 560°C to achieve a hardness of 44 HRc.



## Heat Treatments

BeyLos®2329 is supplied in the annealed or in the pre-hardened condition, depending on the application. We suggest applying the following parameters if a different hardness is required or if heat treatment is needed. This information is only indicative and must be adapted depending on the different heat treatment facilities employed and on the thickness of the bar.

### Soft annealing

<b>Suggested temperature</b>	<b>700°C</b>
<b>Heating</b>	Maximum 50°C/h
<b>Soaking time</b>	60 min every 25 mm thickness
<b>Cooling</b>	In the furnace at less than 20° C/hr to <b>500° C</b> , then at room temperature

Soft annealing is recommended if optimum machinability of the material is important. After soft annealing a hardness of around 220 HB is achieved.

### Stress Relieving

<b>Suggested temperature</b>	<b>650 °C</b>
<b>Heating</b>	Maximum 100°C/h
<b>Soaking time</b>	60 min every 50 mm thickness
<b>Cooling</b>	Slow in the furnace at max 25 °C/h to <b>200°C</b> , then at room temperature

If the suggested temperature is lower than the tempering temperature, the stress relieving temperature will be 50° C lower than the tempering temperature previously applied.

Stress relieving is recommended where it is necessary to eliminate residual stresses induced by mechanical working or by a preceding heat treatment.

## Hardening

Hardening should be carried out after the material has been pre-heated according to the following table.

<b>First pre-heating temperature</b>	<b>550°C</b>
<b>Soaking time</b>	60 min every 25 mm thickness

<b>Austenitising temperature</b>	<b>870°C</b>
<b>Soaking time</b>	60 min every 25 mm thickness
<b>Cooling</b>	Air or vacuum cooling salt bath or polymer in H <sub>2</sub> O


We suggest to carry out the hardening on material supplied in the annealed condition and to temper the material immediately afterwards. The suggested rate of heating is less than or equal to 30 °C.

## Tempering

The tempering temperature to be applied to the material depends on the required mechanical properties. A second temper at a temperature of 30-50° C below the maximum temperature previously applied will function as a stress relieving cycle.

<b>Suggested temperature</b>	Depending on the required mechanical properties. See tempering curve
<b>Heating</b>	Less than or equal 30 ° C/h
<b>Soaking time</b>	60 min every 25 mm thickness
<b>Cooling</b>	At room temperature

In any case, other properties can be analyzed and studied deeper by Lucchini RS on specific Customer request: please consult Lucchini RS specialists of MET Department.



Tempering curve of a sample which has been austenitised at 870 °C and quenched.

## Variation in dimensions during heat treatment

During the heat treatment of BeyLos®2329 the phase transformation points are exceeded. Inevitably this causes a variation in the volume of the material. For this reason we recommend leaving enough allowance to compensate for the change of dimension due to heat treatment. All the corners should be rounded off.

## Nitriding

The purpose of nitriding is to increase the resistance of the material to wear and abrasion.

This treatment is very useful for components where high performance is necessary, as it extends the life of the material.


We suggest nitriding the component in the hardened and tempered condition.

The tempering temperature must be at least 50°C higher than the nitriding temperature.


Modern nitriding processes allow the original dimensions of the component to be maintained.

We recommend heat treating the component in the finish machined condition.

**CCT curve**



**Microstructure of BeyLos®2329**



Microstructure of a pre-hardened BeyLos®2329 of tempered martensite.

## Quick comparison guide among the different grades for Hot Work tools

The following table shows a quick comparison among the most important characteristics of the pre-hardened grades normally applied as Hot Work Tools.

<b>Excellent</b>	<b>4</b>
<b>Very Good</b>	<b>3</b>
<b>Good</b>	<b>2</b>
<b>Normal</b>	<b>1</b>
<b>Unsuitable</b>	<b>0</b>

Lucchini RS Hot Work tool Steel Family															
Special features and delivered conditions	KEY LOS	Annealed Not Corrosion Resistant													
		BEYLOS								ESKYLOS					
		6959	2329	2711	2714	2004	2343	2344	2365M	2367	6959	2004	2343	2344	2365M
HB in surface in Annealed condition	<220	<220	<250	<250	<220	<220	<220	<220	<220	<220	<220	<220	<220	<220	<220
HB in surface Hardened after machining	370-410	370-410	370-410	370-410	400-450	400-450	400-450	400-450	400-450	370-410	400-450	400-450	400-450	400-450	400-450
Maximum thickness [mm]	500	600	500	700	500	500	500	500	500	500	500	500	500	500	500
Hardness and Wear Resistance	3	3	3	3	4	4	4	4	4	3	4	4	4	4	4
Degree of Through Hardening in the section	4	2	3	3	3	3	3	3	3	4	3	3	3	3	3
Toughness	4	1	4	4	3	3	2	2	2	4	3	3	2	2	2
Machinability after Annealing	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3
Machinability after Hardening	1	2	1	1	1	1	1	1	1	1	1	1	1	1	1
Etch-Grainability	2	2	2	2	2	2	2	2	2	4	4	4	4	4	4
Polishability	2	2	2	2	2	2	2	2	2	4	4	3	3	4	3
Repair by Welding	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Thermal Conductivity	2	2	2	2	1	1	1	1	1	2	1	1	1	1	1
Corrosion Resistance	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0
		4 Excellent	3 Very Good	2 Good	1 Normal	0 Unsuitable									

The information and the data presented here are typical or average values and are not a guarantee of maximum or minimum values.

Applications specifically suggested for materials described herein and in the quick comparison guide among the different grades are made solely for the purpose of illustration to enable the reader to make his own evaluation and are not intended as warranties, either express or implied, of fitness for these or other purposes.

## Guidance for machining

The following parameters are indicative only and must be adapted to the particular application and to the machinery employed. The data refer to material in the annealed condition. Hardness 220 HB max.

### Turning

	Rough		Finish machining	
Type of insert	P20-P40 coated	HSS	P10-P20 coated	Cermet
$V_c$ Cutting speed [m/min]	170 ÷ 220	(*)	200 ÷ 250	240 ÷ 300
$a_r$ Cutting depth [mm]	1 ÷ 5	(*)	< 1	< 0,5

### Milling

	Rough machining		
Type of insert	P25-P35 not coated	P25-P35 coated	HSS
$V_c$ Cutting speed [m/min]	140 ÷ 200	180 ÷ 260	(*)
$f_z$ Feed [mm]	0,15 ÷ 0,3	0,15 ÷ 0,3	(*)
$a_p$ Cutting depth [mm]	2 ÷ 4	2 ÷ 4	(*)

	Pre-finishing		
Type of insert	P10-P20 not coated	P10-P20 coated	HSS
$V_c$ Cutting speed [m/min]	160 ÷ 240	240 ÷ 280	(*)
$f_z$ Feed [mm]	0,2 ÷ 0,3	0,2 ÷ 0,3	(*)
$a_p$ Cutting depth [mm]	1 ÷ 2	1 ÷ 2	(*)

	Finish machining		
Type of insert	P10-P20 not coated	P10-P20 coated	Cermet P15
$V_c$ Cutting speed [m/min]	200 ÷ 260	240 ÷ 300	240 ÷ 330
$f_z$ Feed [mm]	0,05 ÷ 0,2	0,05 ÷ 0,2	0,05 ÷ 0,2
$a_p$ Cutting depth [mm]	0,5 ÷ 1	0,5 ÷ 1	0,3 ÷ 0,5

## Drilling

BAYLOS 2329			
Type of tool tip	tip with interchangeable inserts	HSS	brazed
$V_c$ Cutting speed [m/min]	190 ÷ 220	(*)	60 ÷ 80
$f_n$ Feed [mm/turn]	0,05 ÷ 0,15	(*)	0,15 ÷ 0,25

(\*)not advisable

## General formulae

BAYLOS 2329		
Type of machining	Drilling	Milling
$n$ : Milling cutter or tip diameter	$\frac{V_c * 1000}{\pi * D_c}$	$\frac{V_c * 1000}{\pi * D_c}$
$V_f$ : Cutting speed [mm/min]	$V_f = f_z * n$	$V_f = f_z * n * z_n$
$f_n$ : Feed per turn [mm/turn]	-	$f_n = \frac{V_f}{n}$
<b>Notes</b>	$D_c$ : Milling cutter or tip diameter [mm] $V_c$ : Cutting speed [m/min] $f_z$ : Feed [mm]	$f_n$ : Milling cutter or tip diameter [mm/turn] $z_n$ : No. of milling cutter inserts

## Approximate equivalent values between hardness and ultimate tensile strength

<b>HB</b>	530	520	512	495	480	471	458	445	430	415	405	390	375
<b>HRC</b>	54	53	52	51,1	50,2	49,1	48,2	47	45,9	44,5	43,6	41,8	40,5
<b>MPa</b>	1.900	1.850	1.800	1.750	1.700	1.650	1.600	1.550	1.500	1.450	1.400	1.350	1.300

<b>HB</b>	360	350	330	320	305	294	284	265	252	238	225	209	195
<b>HRC</b>	38,8	37,6	35,5	34,2	32,4	31	29	27	--	--	--	--	--
<b>MPa</b>	1.250	1.200	1.150	1.100	1.050	1.000	950	900	850	800	750	700	650

## Welding

Welding of BeyLos®2329 can give good results if the recommended procedure is followed. Being steel with high carbon equivalent content, BeyLos®2329 is very sensitive to cracking. We recommend carrying out pre-heating and heat treatment after welding.

<b>Condition of material</b>	Annealed with hardness 220 HB max	
<b>Welding technique</b>	TIG	MMA
<b>Pre-heating at</b>	250÷300 °C	
<b>Recommended heat treatment</b>	Heating of the material at 700 °C, cooling in the furnace to 600 °C at a rate of 20 °C/h, cooling at room temperature	
<b>Condition of material</b>	Hardened and tempered	
<b>Welding technique</b>	TIG	MMA
<b>Pre-heating at</b>	250÷300 °C	
<b>Recommended heat treatment</b>	550 °C or 50 °C lower than the tempering temperature previously applied	

## Electrical Discharge Machining (EDM)

BeyLos®2329 can be machined by EDM to obtain complex shape.

Afterwards it is advisable to stress relieving the material.

## Chrome Plating

BeyLos®2329 can be Chrome plated in order to enhance the mechanical characteristics on the surface.

Within 4 hours of Chrome plating, in order to prevent Hydrogen embitterment it is advisable to carry out heat treatment at 200 °C for about 4 hours.

## Photo-engraving

Thanks to modern production processes and to the low Sulphur content, BeyLos®2329 is suitable for photo-engraving to obtain various patterns.

## Polishing

BeyLos®2329 is particularly suitable for polishing.

## Process and materials selection for product recyclability

According to the potential of steel recycling, Lucchini RS is adopting a strategy for environmental excellence in designing and manufacturing of its tool steel grades, putting eco-effectiveness into practice.

The main adopted steps are:

-conducting an environmental assessment on processes and products, with the minimum use of virgin materials and non-renewable forms of energy;

-moving toward zero-waste manufacturing processes, considering that the ultimate destiny of a scrapped steel mould becomes food for the next steel making process, that is the "waste equals food" philosophy;

-conducting a life cycle assessment for-each product and process, minimizing the environmental cost of product and service over its entire life cycles, from creation to disposal, that is the "Cradle to Cradle" philosophy.



Via G. Paglia, 45

24065 Lovere (BG) - ITALY

Phone + 39 035 963492

Fax + 39 035 963552

Web <http://www.lucchinirs.it>

E-mail [toolsteels@lucchinirs.it](mailto:toolsteels@lucchinirs.it)