



KEYLOS[®] 35 EVO

| VALUE IN PERFORMANCE

**THE CUSTOMISED SOLUTION
FOR PLASTIC MOULDS**



**FORGING
VALUES
IN PERFORMANCE**

IMPROVEMENT
COURAGE
PEOPLE
PASSION
SPIRIT
GROUP
CUSTOMER
SUCCESS

GROUP
LUCCHINI RS

General characteristics

KEYLOS[®] 35 EVO represents the latest improvement of Lucchini RS steel grades traditionally dedicated to the plastic injection and compression moulds, developed with specific focus on the big sized blocks.

Thanks to the accurate design of its chemical composition and to the special heat treatment procedure, KEYLOS[®] 35 EVO is characterized by excellent hardenability across the block, minimizing the decrease of the hardness from surface to core, excellent ratio of hardness to toughness, very high thermal conductivity and excellent finishing properties.

KEYLOS[®] 35 EVO steel was developed by Lucchini RS from the standard steel grade 1.2738 HH, widely used and appreciated for its characteristics of high hardness, excellent toughness and homogeneity, further improved by Lucchini RS experience in injection moulding field.

KEYLOS[®] 35 EVO represents, in fact, a further step in the continuous improvement of 1.2738 HH steel grade developed by Lucchini RS over time.

According to the low Carbon Equivalent content, the weldability is excellent and KEYLOS[®] 35 EVO is easier and safer in case of welding repair.

Delivery conditions

KEYLOS[®] 35 EVO is supplied in quenched and tempered condition and it is the best option for the large dimension blocks with thickness up to 1300 mm.

The surface hardness is 320 – 360 HB and the mid-thickness hardness value is guaranteed in section up to 1300 mm, according to the following correlation: $(HB_{\text{Surface, min required}} - HB_{\text{Core}}) \leq 20HB$

Main features

- Homogeneous hardness across the blocks;
- excellent toughness;
- excellent thermal conductivity;
- excellent wear resistance;
- good machinability;
- very good polishability;
- excellent for photo-engraving;
- excellent for nitriding and hard chromium plating;
- improved weldability.

Main application

- Big sized injection and compression moulds for exterior and interior plastic components for automotive sector: in particular cavities for bumpers and dashboards.
- Home appliances: rear TV housing, copier housing, crates, dustbins, chairs et cetera.

Chemical analysis

	Range	C [%]	Si [%]	Mn [%]	Cr [%]	Mo [%]	Ni [%]	V [%]
KEYLOS[®] 35 EVO Alloying [% in weight]	min	0,22	0,15	1,20	1,20	0,45	0,80	0,10
	max	0,32	0,55	1,60	1,60	0,70	1,50	0,20

Comparison with international classifications:

W. Nr. 1.2738 mod. HH

AISI P20 mod. HH

DIN: 26MnCrNiMo7

Physical and mechanical properties



Main physical properties

KEYLOS[®] 35 EVO	20°C	250°C	500°C
Young modulus E [MPa]	209	193	176
Coefficient of linear thermal expansion α [10 ⁻⁶ /K]	-	12,6	14,4
Thermal conductivity λ [W/mK]	34,6	34,1	33,9

Main mechanical properties


KEYLOS[®] 35 EVO	20°C	200°C
Ultimate tensile strength UTS [MPa]	1085	925
Yield strength YS [MPa]	985	785
Elongation A [%]	18	19
Reduction in area Z [%]	53	55

Hardness profile




Microstructure

The main microstructure of KEYLOS[®] 35 EVO is tempered martensite.




100x




500x

Remark: the above data are representative of the typical behaviour of a 1100 mm thick block made in KEYLOS[®] 35 EVO and are reported for information only

Surface hardness vs tempering temperature



Toughness (Charpy V-notch test at 20°C) vs tempering temperature




Heat treatment

KEYLOS 35[®] EVO is supplied in quenched and tempered conditions with no need for additional heat treatment operations.

However, if different hardness/heat treatment procedure are required, we recommend the following parameters.

Note that the reported data are for information purpose only and must be adjusted to the heat treatment facility and the dimensions of the block therefore, before carrying out any heat treatment operation, it is strongly recommended to contact Lucchini RS for help and support.

Continuous cooling transformation curve (CCT)



Soft annealing

Suggested temperature	700 °C
Soaking time	60 min every 25 mm thickness
Cooling	Slow cooling in furnace (20°C/h)

Soft annealing is useful to improve machinability reducing hardness at 250 HB.

Stress relieving

Suggested temperature	500 °C
Soaking time	60 min every 25 mm thickness
Cooling	Slow cooling in furnace (20°C/h)

Stress relieving is recommended to reduce the tensions generated by certain manufacturing operations (e.g. machining) without affecting the hardness in the as-delivered conditions.

If the suggested temperature is lower than the tempering temperature, the stress relieving temperature will be 50° C lower than the tempering temperature previously applied.

Hardening

Suggested temperature	900 °C
Soaking time	60 min every 25 mm thickness
Cooling	Polymer or water quench

Tempering

Suggested temperature	Depending on the required mechanical properties
Soaking time	120 min every 25 mm thickness
Cooling	Room temperature

The tempering temperature should be selected from the graph "Tempering curve" reported above.

After tempering we suggest to carry out stress relieving at temperature 50° C lower than the last tempering temperature.

Induction hardening

KEYLOS[®] 35 EVO is suitable for induction hardening. We recommend cooling at room temperature and tempering after induction hardening.

Nitriding

KEYLOS[®] 35 EVO is suitable for ionic and gas nitriding. This treatment is very useful for moulds subjected to extremely stressful applications.

The increase of the surface hardness, following nitriding, extends the component life cycle.

Other properties can be deeper analysed against specific Customer request: please contact our Metallurgy Department.

Up-to-date nitriding procedures allow to minimize the dimensional variation of the piece.

We recommend to heat treat the piece in finish machined condition.

In order to obtain the best results, we recommend the following manufacturing procedure:

- rough machining;
- stress relieving;
- finish machining;
- nitriding.

Polishing and photo-engraving

KEYLOS[®] 35 EVO is the suitable material when polishing and photoengraving are needed. Thanks to its integrated manufacturing process, those material manufactured by Lucchini RS are characterized by a high degree of purity.

Polishing for graining: **4 Excellent**

Suitability for medium gloss polishing: **4 Excellent**

Suitability for mirror polishing: **3 Very Good**

Suitability for engraving: **4 Excellent**

Rating scale:

4 Excellent – **3 Very good** – **2 Good** – **1 Normal** – **0 Unsuitable**

Guidance for machining

The following parameters are approximate only and must be adjusted to the specific application and machine tool.

Turning

Type of insert	Rough machining		Finish machining	
	P20-P40 coated	HSS	P10-P20 coated	Cermet
V _c cutting speed [m/min]	150 ÷ 190	(*)	190 ÷ 230	260 ÷ 320
a _r cutting depth [mm]	5	(*)	< 1	< 0,5

Milling

Type of insert	Rough machining		
	P25-P35 not coated	P25-P35 coated	HSS
V _c cutting speed [m/min]	120 ÷ 140	160 ÷ 180	(*)
f _z feed [mm]	0,15 ÷ 0,3	0,15 ÷ 0,3	(*)
a _r cutting depth [mm]	2 ÷ 4	2 ÷ 4	(*)

Type of insert	Pre-finishing		
	P10-P20 not coated	P10-P20 coated	HSS
V _c cutting speed [m/min]	140 ÷ 160	180 ÷ 200	(*)
f _z feed [mm]	0,2 ÷ 0,3	0,2 ÷ 0,3	(*)
a _r cutting depth [mm]	< 2	< 2	(*)

Type of insert	Finishing		
	P10-P20 not coated	P10-P20 coated	Cermet P15
V _c cutting speed [m/min]	200 ÷ 240	250 ÷ 270	300 ÷ 340
f _z feed [mm]	0,05 ÷ 0,2	0,05 ÷ 0,2	0,05 ÷ 0,2
a _r cutting depth [mm]	0,5 ÷ 1	0,5 ÷ 1	0,3 ÷ 0,5

(*) not advisable

Drilling

Type of insert	tip with interchangeable inserts	HSS	brazed tip
V_c cutting speed [m/min]	130 ÷ 160	(*)	90 ÷ 120
f_z feed per turn [mm/turn]	0,05 ÷ 0,15	(*)	0,15 ÷ 0,25

(*) not advisable

General formulae

Type of machining	Drilling	Milling
n: number of turns of mandrel	$V_c * 1000 / \pi * D_c$	$V_c * 1000 / \pi * D_c$
V_f : feed speed [m/min]	$V_f = f_z * n$	$V_f = f_z * n * z_n$
f_z feed per turn [mm/turn]	-	$f_n = V_f / n$
Note	D_c : Milling cutter or tip diameter [mm] V_c : cutting speed [m/min] f_z : feed [mm]	f_n : feed per turn [mm/turn] z_n : No. of milling cutter inserts

Welding

In order to obtain the best results, we recommend the following procedure:

Welding technique	TIG	MMA
Pre-heating at	250 - 300 °C	
Heat treatment	Stress relieving (see heat treatment paragraph)	

Electrical Discharge Machining (EDM)

KEYLOS[®] 35 EVO can be machined by EDM to obtain complex shape. Afterwards we advise to carry out the stress relieving procedure

Process and materials selection for product recyclability

According to the potential of steel recycling, Lucchini RS is adopting a strategy for environmental excellence in designing and manufacturing its tool steel grades, putting eco-effectiveness into practice.

The main adopted steps are:

- to carry out an environmental assessment on processes and products, with the minimum use of virgin materials and non-renewable forms of energy;
- to move toward zero-waste manufacturing processes, considering that the ultimate destination of scrapped steel moulds becomes food for the next steel making process, that is the "waste equals food" philosophy;
- to carry out a life cycle assessment for each product and process, minimizing the environmental cost of product and service over its complete life cycles, from creation to disposal, that is the "Cradle to Cradle" philosophy

Quick comparison guide among the different steel grades

The following table shows a quick comparison among the main characteristics of pre-hardened steel grades traditionally used in plastic moulding.

		Tool Steels for plastic											
		LUCCHINI							KEYLOS				
		1730	7225	2311	2312	2738	P20	P20HH	UP	30	35	35 EVO	40 EVO
HB	Min	-	220	280	280	290	290	320	280	290	320	320	360
	Max	250	270	330	330	340	330	360	330	330	360	360	400
Maximum thickness [mm]		300	400	500	500	1.000	1.000	1.000	800	1.000	1.000	1.300	800
Wear Resistance		1	1	2	2	2	2	3	2	2	3	3	4
Through Hardening in the section		1	1	2	2	3	3	3	3	4	4	4	4
Toughness		1	2	2	2	2	2	2	2	3	3	3	3
Machinability		3	2	2	3	2	2	2	2	2	2	2	2
Polishing		1	1	2	0	2	2	2	2	3	3	3	3
Photo-engraving		2	2	3	0	3	3	3	3	4	4	4	4
Welding (reparing)		3	3	2	2	2	3	3	2	3	3	3	3

4 Excellent 3 Very Good 2 Good 1 Normal 0 Unsuitable

Lucchini RS S.p.A. All rights reserved. All contents of this document and all the related industrial and intellectual rights belongs exclusively to Lucchini RS S.p.A. that owns and manages the original version of it. The reproduction, disclosure, dissemination and/or changing of this document, in whole or in part, as well as the utilization of its content and/or the communication there of to third party without express written authorization of Lucchini RS S.p.A. are prohibited.

Via Giorgio Paglia, 45
24065 LOVERE (BG) - Italy
Phone +39 035 963724



www.lucchinirs.com

GROUP
LUCCHINI *RS*